



## TECHNICAL INFORMATION SHEET

### HARRIS SAFETY SILV 30T BRAZING FILLER METAL

#### NOMINAL CHEMICAL COMPOSITION%:

Silver	29-31 %
Copper	34-36 %
Zinc	32-34 %
Tin	1.5-2.5 %
Other (Total)	0.15

#### TYPICAL PHYSICAL PROPERTIES:

Solidus	1205°F (650°C)
Liquidus	1390°F (754°C)

#### BRAZING PROPERTIES:

Safety Silv 30T is a free flowing cadmium free, silver brazing alloy, suitable for brazing copper, brass, steel and stainless steel. It has good corrosion resistance, and will likely find increasing applications into areas legislation forbids the use of cadmium bearing grades of alloy.

#### CORROSION RESISTANCE

Generally similar to the copper base metal, but zinc containing alloys, including Safety Silv 30T, should not be used if the braze is exposed to concentrated corrosive liquid for a long period of time

#### AVAILABLE FORMS

Standard wire diameters, preform rings.

#### RECOMMENDED FLUX:

Stay Silv white flux, or where heating cycles are extended Stay Silv Black flux.

#### SPECIFICATION COMPLIANCE:

ANSI/AWS A5.8, ASME SFA 5.8, Class BAg-28,

#### SAFETY INFORMATION:

**WARNING: PROTECT** yourself and others. Read and understand this information.

**FUMES AND GASES** can be hazardous to your health.

**HEAT RAYS**, (infrared radiation) from flame or hot metal can injure eyes.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDS), and your employer's safety practices.
- Keep your head out of fumes.
- Use enough ventilation, exhaust at the flame, or heat source, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- See American National Standard Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society, 8669 Doral Blvd., Doral, Florida 33166; OSHA Safety and Health Standards, available from the U.S. Government Office, Washington, DC 20402.

#### STATEMENT OF LIABILITY- DISCLAIMER

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. The Harris Products Group and its affiliates shall have no liability in respect thereof.

#### THE HARRIS PRODUCTS GROUP

A LINCOLN ELECTRIC COMPANY

4501 Quality Place • Mason, OH 45040 U.S.A Tel: 513-754-2000 Fax: 513-754-6015

Additional information available at our web site: [www.harrisproductsgroup.com](http://www.harrisproductsgroup.com)