



TECHNICAL INFORMATION SHEET

SAFETY SILV® 35 BRAZING FILLER METAL

NOMINAL CHEMICAL COMPOSITION%:

Silver	34-36
Copper	31-33
Zinc	31-35
Other (Total)	0.15

TYPICAL PHYSICAL PROPERTIES:

Solidus	1265°F (685°C)
Liquidus	1390°F (754°C)
Brazing Range	1390°F- 1545°F (755°C -840°C)
Electrical Conductivity	18.9 (%IACS)
Density	4.79 (t.o./cu.in.).

BRAZING PROPERTIES:

A lower temperature silver brazing alloy with a medium melting range. Safety Silv 35 is suitable for joining steel, copper and most brasses. Safety Silv 35 is cadmium free, making it useful for applications where cadmium fume must be eliminated from the brazing environment.

AVAILABLE FORMS

Standard wire diameters in wire, rod, and preform rings.

RECOMMENDED FLUX:

Stay-Silv® white flux is suitable for many applications. Stay-Silv® black brazing flux is often used if brazing stainless steel or where heating cycles are prolonged or focused as in induction brazing. Harris ECO SMART® boric acid free flux, (powder or paste), is an excellent choice to promote sound brazed assemblies and comply with European REACH requirements.

SPECIFICATION COMPLIANCE:

ANSI/AWS A5.8, ASME SFA5.8 Class BAg-35
ISO 17672 Ag 235

SAFETY INFORMATION:

WARNING: PROTECT yourself and others. Read and understand this information.
FUMES AND GASES can be hazardous to your health.
HEAT RAYS, (infrared radiation) from flame or hot metal can injure eyes.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDS), and your employer's safety practices.
- Keep your head out of fumes.
- Use enough ventilation, exhaust at the flame, or heat source, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- See American National Standard Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society, 8669 Doral Blvd., Doral, Florida 33166; OSHA Safety and Health Standards, available from the U.S. Government Office, Washington, DC 20402.

STATEMENT OF LIABILITY- DISCLAIMER

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. The Harris Products Group and its affiliates shall have no liability in respect thereof.

THE HARRIS PRODUCTS GROUP

A LINCOLN ELECTRIC COMPANY

4501 Quality Place • Mason, OH 45040 U.S.A Tel: 513-754-2000 Fax: 513-754-6015
Additional information available at our web site: www.harrisproductsgroup.com